



# PcBN

## Cutting Tools



SBC ■ PBC ■ Sandwich  
coated ■ uncoated



**AYMA**  
HERRAMIENTAS

Turning ☒ Grooving ☒ Boring ☒ Milling

C1048.02 11/11IN



ultrahard

cutting materials

## Application field

**PBC 10S** - for high cutting speed and long tool life  
in machining of grey cast irons


**For example:** drive wheel, GG 25, diameter 480 mm

**Used insert type:** DCGW 11T308-D-10S-2MC

**Superfinishing:**  $V_c = 1.430$  m/min,  $a_p = 0,3 - 0,5$  mm,  $f = 0,20$  mm

**Tool life:** 280 parts

**For comparison only:** coated carbide insert: 26 parts,  $V_c = 300$  m/min



**PBC 15S** - for extremely high tool life  
in machining of nodular cast irons


**For example:** bearing, GGG 60, diameter 200 mm

**Used insert type:** DCGW 11T308-D-15S-2MC

**Superfinishing:**  $V_c = 900$  m/min,  $a_p = 0,3$  mm,  $f = 0,28$  mm

**Tool life:** 120 parts

**For comparison only:** coated carbide insert: 15 parts,  $V_c = 220$  m/min



**PBC 25S** - favoured in continuous cut,  
Hardness: HRc 48 - 62, best surface finish

**For example:** drive shaft HRc 60, Mat: 1.2332 - 47CrMo4

**Used insert Type:** CNGA 120408-E-25S-4SC

**Superfinishing:**  $V_c = 180$  m/min,  $a_p = 0,25$  mm  $f = 0,08$  mm

**Surface finish:**  $R_a 0,18 \mu$

**Tool life:** turning length = 3.218 m



**PBC 40S** - favoured in interrupted cut  
Hardness: HRc 48 - 65, highest tool life


**For example:** Gear HRc 58, Mat: 1.3523 - 19MnCr5

**Used insert type:** CNGA 120408-G-40S-4SC

**Superfinishing:**  $V_c = 230$  m/min,  $a_p = 0,22$  mm,  $f = 0,16$  mm

**Surface finish:**  $R_a 0,40 \mu$

**Tool life:** turning length = 4.280 m






## Content


### Technology

Sandwich - The cost killer .....	Page	3
Groups of cutting material .....	Page	4
Material grade overview .....	Page	5
PcBN-cutting materials – coated .....	Page	6
PcBN-cutting materials – uncoated .....	Page	7
Tipping modifications of all coated grades – ISO-BECKER .....	Page	8
Tipping modifications of all uncoated grades with carbide layer ISO-BECKER.....	Page	9
Tipping modifications of all uncoated solid grades without carbide layer ISO-BECKER.....	Page	10
Tipping modifications of all our PcBN-grades with maximum depth of cut .....	Page	11
Wiper-geometry and surface finish .....	Page	12
Positive top rake geometries.....	Page	13
Cutting data .....	Pages	14 – 17
ToolScout.....	Pages	18 – 19
ISO-insert nomenclature and order designation.....	Pages	20 – 21



### Turning

ISO-inserts.....	Pages	22 – 45
------------------	-------	---------




### Grooving

FormCut grooving system with inserts .....	Pages	46 – 49
--	-------	---------



### Boring

MiniCut-boring system with inserts .....	Pages	50 – 53
--	-------	---------



### Milling

ISO-milling inserts .....	Pages	54 – 55
---------------------------	-------	---------



Important information .....	Page	56
-----------------------------	------	----





cutting materials

ultrahard


TECHNOLOGY

TURNING

GROOVING

BORING

MILLING



## Dear customers and business partners,

The great challenges of future cutting techniques can only be mastered by ultra-hard cutting materials. For decades we have been pioneering the development and production of efficient cutting tools made of diamond and PcBN. Our tools are practically applied in all industries world-wide, for example in automotive engineering and associated suppliers, aircraft and engine construction, mechanical engineering, precision engineering and medical engineering.

On the following pages we will introduce our broad range of PcBN cutting tools. We have uniformly put the coated and uncoated tools together into one catalogue. This adds up to a comprehensive selection covering practically every application possible.

- 14 different PcBN grades
- Instant delivery ex stock
- Please take note of our regrinding service

In case of suggestions or queries in order to increase performance and improve your product quality, we will gladly be at your service.

Please take note of our new catalogue on our cutting tools tipped with our 5 different ultrahard diamond cutting materials.

*Sincerely,  
Becker Diamantwerkzeuge GmbH*

ultrahard





cutting materials



## Sandwich – The Cost Killer

Besides the manufacturing of double fullface inserts we cut the new sandwich blanks into rectangular segments and braze them into the correspondingly prepared carbide blanks for negative inserts. Thus we automatically receive 2 cutting edges per brazed

segment each of which has a large volume of PcBN cutting material. This manufacturing process both saves a huge amount of resources and makes a lot of sense economically. We also point out the possibility of regrinding



We manufacture all shapes of negative inserts in multiple corner tipping or double fullface type from these blanks. As the production costs of these sand-

wich blanks are nearly identical to the established, one-sidedly tipped PcBN blanks there is a considerable price advantage per cutting edge or total layer.

The new sandwich blanks are manufactured in 4 different grades:

PBC-10S (BH-C), 95 % content, special grade for machining grey cast iron und super alloys.
PBC-15S (BH-C), 90 % content, special grade for machining nodular cast iron and sintered powdered steel.
PBC-25S (BL-C), 65 % content, special grade for hard turning, favoured in continuous cut.
PBC-40S (BL-C), 55 % content, special grade for hard turning, favoured in interrupted cut.

The development of ultrahard cutting materials is practiced intently on a world-scale and therefore constant progress in the machining is guaranteed. We

have committed ourselves to these developments to standardly offer to our customers the most suitable ultrahard cutting materials, tools and tool systems.



ultrahard

cutting materials

TECHNOLOGY


TURNING

GROOVING

BORING

MILLING

## Groups of cutting materials (DIN ISO 513)



Additional ISO designation codes for carbide (also Cermet) and ceramics have been added to the DIN ISO 513 (2001) standard. Furthermore new ident letters for the ultrahard cutting materials polycrystalline cubic boron nitride, monocrystalline and polycrystalline diamond have been introduced.


<p><b>HW</b> = Uncoated carbide</p> <p><b>HF</b> = Fine grained carbide</p> <p><b>HT</b> = Cermet, TiC or TiN</p> <p><b>HC</b> = Carbide / Cermet as above, but coated</p>	<p><b>DM</b> = Monocrystalline diamond</p> <p><b>DP</b> = Polycrystalline diamond-compound</p> <p><b>PD</b> = CVD - thickfilm diamond</p>
<p><b>CA</b> = Ceramics, main content <math>Al_2O_3</math></p> <p><b>CM</b> = Mixed ceramics, main content <math>Al_2O_3</math>, plus components other than oxides</p> <p><b>CN</b> = Siliconnitride ceramics, main content <math>Si_3N_4</math></p> <p><b>CR</b> = Ceramics, main content <math>Al_2O_3</math> reinforced</p> <p><b>CC</b> = Ceramics as above, but coated</p>	<p><b>BL</b> = Polycrystalline Cubic Boron Nitride with low content of CBN (40 - 65%)</p> <p><b>BH</b> = Polycrystalline Cubic Boron Nitride with high content of CBN (70 - 95%)</p> <p><b>BC</b> = Polycrystalline Cubic Boron Nitride as above, but coated</p>

ultrahard

cutting materials



## Material grade overview





ultrahard

cutting materials

## ■ PcBN-cutting materials - coated

Grades - Application

Becker	ISO	Composition	Application
<b>PBC-10S</b>	<b>BH-C</b>	Coated PcBN-grade with very high CBN-content (95%) in sandwich and standard design, fine grit size (1 – 1.5 $\mu$ ).	Grey cast iron (GG25) Sintered powdered steel Super alloys ap = 0.1 – 0.7 mm
<b>PBC-15S</b>	<b>BH-C</b>	Coated PcBN-grade with high CBN content (90%) in sandwich and standard design, super fine grit size (0.75 $\mu$ ).	Nodular cast iron Grey cast iron Sintered powdered steel Super alloys ap = 0.05 – 0.7 mm
<b>PBC-25S</b>	<b>BL-C</b>	Coated PcBN-grade with low CBN content (65%) in sandwich and standard design, fine grit size (1 – 2 $\mu$ ). Ideal for hard turning in continuous cut.	Hard turning, dry + wet HRc = 48 - 62 ap = 0.02 – 0.4 mm Ra = 0.2 – 3.2 $\mu$
<b>PBC-40S</b>	<b>BL-C</b>	Coated PcBN-grade with low CBN content (55%) in sandwich and standard design, super fine grit size (0.75 $\mu$ ). Grade for slightly- to heavily-interrupted cut.	Hard turning, dry + wet HRc = 48 - 65 ap = 0.05 – 0.4 mm Ra = 0.1 – 3.2 $\mu$
<b>SBC-25C</b>	<b>BL-C</b>	Coated solid PcBN-grade with low CBN content (65%), fine grit size (3 $\mu$ ). Grade for hard turning in continuous cut and higher depth of cut.	Hard turning, dry + wet HRc = 48 - 65 ap = 0.04 – 0.8 mm Ra = 0.2 – 3.2 $\mu$
<b>SBC-40C</b>	<b>BL-C</b>	Coated solid PcBN-grade with low CBN content (65%), super fine grit size (1 $\mu$ ). Grade for hard turning in slightly to heavily interrupted cut and higher depth of cut.	Hard turning, dry + wet HRc = 48 - 65 ap = 0.05 – 0.8 mm Ra = 0.1 – 3.2 $\mu$





## ■ PcBN-cutting materials - uncoated

Grades - Applications

Becker	ISO	Composition	Application
SBC- 1	BH	Uncoated solid PcBN-grade with high CBN-content (90%), coarse grit size (8 – 12 $\mu$ ). Highest compression strength and thermal stability of all PcBN-grades.	Chilled cast iron Ni-hard Grey cast iron $a_p = 0.5 - 10$ mm
SBC-10	BH	Uncoated solid PcBN-grade with high CBN content (80%), fine grit size (3 $\mu$ ).	Grey cast iron Super alloys Sintered powdered steel $a_p = 0.3 - 8$ mm
SBC-25	BL	Uncoated solid PcBN-grade with low CBN content (65%), fine grit size (3 $\mu$ ). Favoured application in continuous cut.	Hard turning, dry + wet HRc = 56 – 65 $a_p = 0.05 - 6$ mm Ra = 0.2 – 3.2 $\mu$
SBC-40	BL	Uncoated solid PcBN-grade with low CBN content (65%), super fine grit size (1 $\mu$ ). For slightly- to heavily-interrupted cut.	Hard turning, dry + wet HRc = 56 – 65 $a_p = 0.05 - 6$ mm Ra = 0.2 – 3.2 $\mu$
PBC-10	BH	Uncoated PcBN-grade with very high CBN content (95%) in standard design. Fine grit size (1 – 1.5 $\mu$ ).	Grey cast iron Super alloys Sintered powdered steel $a_p = 0.1 - 0.4$ mm
PBC-15	BH	Uncoated PcBN-grade with high CBN content (90%) in standard design. Super fine grit size (0.75 $\mu$ ).	Nodular cast iron Sintered powdered steel Super alloys Grey cast iron $a_p = 0.05 - 0.4$ mm
PBC-25	BL	Uncoated PcBN-grade with low CBN content (65%) in standard design. Fine grit size (3 $\mu$ ), for continuous and very slightly-interrupted cut.	Hard turning, dry + wet HRc = 52 - 65 $a_p = 0.05 - 0.4$ mm Ra = 0.2 – 3.2 $\mu$
PBC-40	BL	Uncoated PcBN-grade with low CBN content (65%) in standard design. Super fine grit size (1 $\mu$ ), for continuous to heavily-interrupted cut.	Hard turning, dry + wet HRc = 54 - 65 $a_p = 0.05 - 0.4$ mm Ra = 0.2 – 3.2 $\mu$








ultrahard

cutting materials

## Tipping modifications

Of all coated grades - ISO-BECKER

ISO	Becker	Design	Grades	Becker	ISO
E	SE		Coated sandwich PcBN grades, double-sided layer thickness approx. 0.7 – 0.8 mm	PBC-10S PBC-15S PBC-25S PBC-40S	BH-C BH-C BL-C BL-C
C	SC		Coated sandwich PcBN grades, layer thickness approx. 0.6 – 0.8 mm	PBC-10S PBC-15S PBC-25S PBC-40S	BH-C BH-C BL-C BL-C
A	MC		Coated standard PcBN grades, layer thickness approx. 0.6 – 0.8 mm	PBC-10S PBC-15S PBC-25S PBC-40S	BH-C BH-C BL-C BL-C
A-S	MC-S		Coated solid PcBN grades, layer thickness approx. 1.2 – 1.3 mm	SBC-25C SBC-40C	BL-C BL-C
A-S	MC-S		Coated solid PcBN grades, layer thickness approx. 1.3 mm	SBC-25C SBC-40C	BL-C BL-C

ultrahard

cutting materials



## Tipping modifications

Of all uncoated grades with carbide layer – ISO-BECKER

ISO	Becker	Design	Grades	Becker	ISO
A	EW		Uncoated standard PcBN grade, carbide reinforced	PBC-10 PBC-15 PBC-25 PBC-40	BH BH BL BL
A	MW		Uncoated standard PcBN grade, carbide reinforced	PBC-10 PBC-15 PBC-25 PBC-40	BH BH BL BL
A	MC		Uncoated standard PcBN grade, carbide reinforced	PBC-10 PBC-15 PBC-25 PBC-40	BH BH BL BL
	GS		Uncoated standard PcBN grade, carbide reinforced	PBC-10 PBC-15 PBC-25 PBC-40	BH BH BL BL
F	VM		Uncoated standard PcBN grade, carbide reinforced	PBC-10 PBC-15 PBC-25 PBC-40	BH BH BL BL

TECHNOLOGY

TURNING

GROOVING

BORING

MILLING



ultrahard

cutting materials

## Tipping modifications

Of all uncoated solid grades without carbide layer ISO-BECKER




















ISO	Becker	Design	Grades	Becker	ISO
A-S	EWS		Uncoated solid PcBN grade, without carbide reinforcement	SBC-1 SBC-10 SBC-25 SBC-40	BH BH BL BL
A-S	MC-S		Uncoated solid PcBN grade, without carbide reinforcement	SBC-1 SBC-10 SBC-25 SBC-40	BH BH BL BL
D	PC-S		Uncoated solid PcBN grade, without carbide reinforcement	SBC-1 SBC-10 SBC-25 SBC-40	BH BH BL BL
D	PC-S4		Uncoated solid PcBN grade, without carbide reinforcement	SBC-1	BH BH BL BL
D	PC-M		Uncoated solid PcBN grade, without carbide reinforcement	SBC-1 SBC-10 SBC-25 SBC-40	BH BH BL BL
D	PC-M4		Uncoated solid PcBN grade, without carbide reinforcement	SBC-1	BH BH BL BL
S	SBC		Uncoated solid PcBN grade, without carbide reinforcement	SBC-1 SBC-10 SBC-25 SBC-40	BH BH BL BL





## Tipping modifications

Of all our PcBN grades with the recommended maximum depth of cut

ISO	Becker	Design	Number of tipped corners			Recommended max. depth of cut
			2	3	4	
A	EW MW MC	 1 tipped corner, carbide reinforced				EW.....ap = 0,4 mm MW.....ap = 0,7 mm MC.....ap = 0,4 mm
A-S	EWS MC-S	 1 tipped corner, solid grades				EWS.....ap = 0,8 mm MC-S.....ap = 0,8 mm
C	SC	 2 tipped corners, carbide reinforced				SC.....ap = 0,7 mm
D	PC-S PC-S4 PC-M PC-M4	 1 tipped edge, solid grades				PC-S.....ap = 2,0 mm PC-S4....ap = 3,0 mm PC-M.....ap = 2,0 mm PC-M4...ap = 3,0 mm
F	VM	 Fullface				VM.....ap = 0,7 mm
E	SE	 Double- sided fullface				SE.....ap = 0,7 mm
S	SBC	 Solid				SBC.....ap = 10 mm




ultrahard

cutting materials

## Wiper Geometry and Surface Finish

The theoretical  $R_t$  surface roughness value can be determined with the radius and the feed rates on hand. The required surface finish can be calculated very precisely in advance, provided all relevant peripheral prerequisites are given. As an example instable conditions of machine and/or workpiece, incorrect chucking, faulty or wrong tool system, wrong cutting speed and depth of cut etc. will all impair the results.

The theoretically computed profile height is generally underrun when hardturning with PcBN. A special cutting mechanism with a high cutting pressure is in operation (self-induced hot-cutting process). This smoothes the theoretical profile with a better surface finish.




All values converted to  $\mu$

$$R_t = \frac{f_2}{8 \times r} \quad r = \frac{f_2}{8 \times R_t} \quad f = \sqrt{8 \times r \times R_t}$$

Theoretical surface roughness	Corner radius					
	$R_t$	Feed rate per revolution ( $f = \text{mm / rev}$ )				
$R_a$	$R_t$	$r = 0,2$	$r = 0,4$	$r = 0,8$	$r = 1,2$	$r = 1,6$
0,6	1,6	$f = 0,05$	$f = 0,07$	$f = 0,10$	$f = 0,12$	$f = 0,14$
1,6	4	$f = 0,08$	$f = 0,11$	$f = 0,15$	$f = 0,19$	$f = 0,23$
3,2	10	$f = 0,12$	$f = 0,17$	$f = 0,24$	$f = 0,29$	$f = 0,36$
6,3	16	$f = 0,16$	$f = 0,22$	$f = 0,30$	$f = 0,37$	$f = 0,45$

A clear improvement of the theoretical surface roughness can be achieved with our WIPER geometry. For the high-performance cutting of all aspects we have developed a number of inserts with WIPER geometry for internal, external and milling processes. This WIPER edge replaces the minor cutting edge reducing its angle to a minimum, whereas it automatically improves the theoretically computed surface roughness by 2 to 4 times.







In practise these are the two possibilities for high-performance and high-tech cutting:

- 1) 2-4x higher feed rate = same surface finish
- 2) same feed rate = 2-4x improved surface finish



## ■ Positive Top Rake Geometries

Top Rake Geometries		PcBN-grades	Applications
	Positive Neutral 1-tipped corner EW-ISO-insert	<b>PBC-10</b> <b>PBC-15</b> <b>PBC-25</b> <b>PBC-40</b>	<b>Low cutting pressure</b> <ul style="list-style-type: none"> <li>■ Thin-walled or instable workpieces</li> <li>■ Internal boring</li> <li>■ Minor tolerances</li> <li>■ Lowest depths of cut</li> </ul>
	Positive Neutral 1-tipped corner EW-MiniCut-insert	<b>PBC-10</b> <b>PBC-15</b> <b>PBC-25</b> <b>PBC-40</b>	<b>Low cutting pressure</b> <ul style="list-style-type: none"> <li>■ Thin-walled or instable workpieces</li> <li>■ Internal boring</li> <li>■ Minor tolerances</li> <li>■ Lowest depths of cut</li> </ul>
	Positive Neutral FullFace MiniCut-insert	<b>PBC-10</b> <b>PBC-15</b> <b>PBC-25</b> <b>PBC-40</b>	<b>Low cutting pressure</b> <ul style="list-style-type: none"> <li>■ Thin-walled or instable workpieces</li> <li>■ Internal boring</li> <li>■ Minor tolerances</li> <li>■ Lowest depths of cut</li> </ul>
	Positive Neutral 1-tipped corner EWS-ISO-insert	<b>SBC-10</b> <b>SBC-25</b> <b>SBC-40</b>	<b>Low cutting pressure</b> <ul style="list-style-type: none"> <li>■ Thin-walled or instable workpieces</li> <li>■ Internal boring</li> <li>■ Minor tolerances</li> <li>■ Lowest depths of cut</li> </ul>

Since their introduction 12 years ago our uncoated PcBN-inserts with positive top rake geometries have captured a considerable potential with our customers. Even though these particular positive top rake geometries are disregarded in any global documentation on cutting technology with PcBN cutting materials, we have been offering those positive insert geometries ex stock with great success.

Those positive geometries are applied for very complex cutting operations both for the machining of cast iron and for hardturning. In particular for very thin-walled and instable workpieces. The possible depths of cut are very low and thus minor tolerances are achieved. As a result of the extremely low cutting pressure, these geometries are preferentially applied for internal turning operations, in parts with unusual projecting lengths.



ultrahard

cutting materials

## ■ Cutting data Application range

Application range for PBC-10S, SBC-1 and SBC-10									
GREY CAST IRON: GG 20 - GG25 - GG30 - GG40									
Vc: m/min	Cutting edge design (T-land + honing)								
	A	B	C	D	E	F	G	H	
Cutting speed ↑ 1750 1500 1250 1000 750 500 300									
	Vc	Vc	Vc	Vc	Vc	Vc	Vc	Vc	Vc
Feed rate	f: 0,02 - 0,25	f: 0,04 - 0,25	f: 0,05 - 0,25	f: 0,05 - 0,40	f: 0,06 - 0,50	f: 0,08 - 0,35	f: 0,10 - 0,35	f: 0,12 - 0,35	Feed rate
Depth of cut PBC-10S	ap: 0,02 - 0,25	ap: 0,03 - 0,3	ap: 0,06 - 0,4	ap: 0,06 - 0,4	ap: 0,08 - 0,5	ap: 0,08 - 0,4	ap: 0,1 - 0,4	ap: 0,12 - 0,4	Depth of cut PBC-10S
Depth of cut SBC-1								ap: 0,15 - 10	Depth of cut SBC-1
Depth of cut SBC-10	ap: 0,05 - 3						ap: 0,3 - 8		Depth of cut SBC-10
Cutting conditions	Continuous to heavily interrupted cut								Cutting conditions

Application range for PBC-10S and PBC-10									
SUPER ALLOYS: Inconel 718, Nimonic, Hastelloy, Waspaloy									
Vc: m/min	Cutting edge design (T-land + honing)								
	A	B	C	D	E	F	G	H	
Cutting speed ↑ 700 600 500 400 300 200 100									
	Vc	Vc	Vc	Vc	Vc	Vc	Vc	Vc	Vc
Feed rate	f: 0,02 - 0,25	f: 0,04 - 0,25	f: 0,05 - 0,25	f: 0,05 - 0,40	f: 0,06 - 0,50	f: 0,08 - 0,35	f: 0,10 - 0,35	f: 0,12 - 0,35	Feed rate
Depth of cut PBC-10S	ap: 0,02 - 0,4	ap: 0,03 - 0,4	ap: 0,06 - 0,4	ap: 0,06 - 0,4	ap: 0,08 - 0,5	ap: 0,08 - 0,4	ap: 0,1 - 0,4	ap: 0,12 - 0,4	Depth of cut PBC-10S
Depth of cut PBC-10S	ap: 0,02 - 0,3						ap: 0,05 - 0,4		Depth of cut PBC-10S
Cutting conditions	Continuous to medium interrupted cut								Cutting conditions





■ Cutting data Application range

Application range for PBC-15S and PBC-15										
NODULAR CAST IRON: GGG30 - GGG40 - GGG50 - GGG60										
Vc: m/min	Cutting edge design (T-land + honing)									
	A	B	C	D	E	F	G	H		
Cutting speed ↑	1750									
	1500	Vc	Vc	Vc	Vc	Vc	Vc	Vc	Vc	Vc
	1250									
	1000									
	750									
	500									
	250									
	Feed rate	f: 0,02 - 0,25	f: 0,04 - 0,25	f: 0,05 - 0,25	f: 0,05 - 0,35	f: 0,06 - 0,35	f: 0,08 - 0,35	f: 0,10 - 0,35	f: 0,12 - 0,35	Feed rate
Depth of cut PBC-15S	ap: 0,05 - 0,25	ap: 0,05 - 0,3	ap: 0,06 - 0,4	ap: 0,06 - 0,4	ap: 0,08 - 0,5	ap: 0,08 - 0,4	ap: 0,1 - 0,4	ap: 0,12 - 0,4	Depth of cut PBC-15S	
Depth of cut PBC-15	ap: 0,04 - 0,25		ap: 0,04 - 0,4						Depth of cut PBC-15	
Cutting conditions	Continuous to medium interrupted cut								Cutting conditions	

Application range for PBC-15S and PBC-15										
SINTERED POWDERED STEEL: Sint D11- Sint D39										
Vc: m/min	Cutting edge design (T-land + honing)									
	A	B	C	D	E	F	G	H		
Cutting speed ↑	800	Vc	Vc	Vc	Vc	Vc	Vc	Vc	Vc	Vc
	700									
	600									
	500									
	400									
	300									
	200									
	Feed rate	f: 0,02 - 0,25	f: 0,04 - 0,25	f: 0,05 - 0,25	f: 0,05 - 0,35	f: 0,06 - 0,35	f: 0,08 - 0,35	f: 0,10 - 0,35	f: 0,12 - 0,35	Feed rate
Depth of cut PBC-15S	ap: 0,02 - 0,4	ap: 0,03 - 0,4	ap: 0,06 - 0,4	ap: 0,06 - 0,4	ap: 0,08 - 0,4	ap: 0,08 - 0,4	ap: 0,1 - 0,4	ap: 0,12 - 0,4	Depth of cut PBC-15S	
Depth of cut PBC-15	ap: 0,02 - 0,3		ap: 0,04 - 0,4						Depth of cut PBC-15	
Cutting conditions	Continuous to heavily interrupted cut								Cutting conditions	



ultrahard

cutting materials

TECHNOLOGY

TURNING

GROOVING

BORING

MILLING

## ■ Cutting data Application range

Application range for PBC-25S and PBC-25											
Hardturning, favoured in continuous cut, $a_p = 0,02 - 0,4$ mm, HRc 48 - 62											
Vc: m/min	Cutting edge design (T-land + honing)								Ra ( $\mu$ )		
	A	B	C	D	E	F	G	H			
Cutting speed ↑ 350 300 250 200 150 100 50										0,1 $\mu$	Surface finish ↑
										0,2 $\mu$	
	Vc	Vc							Ra	0,4 $\mu$	
	Ra	Ra	Vc	Ra	Vc	Ra	Vc	Ra	Vc	0,8 $\mu$	
										1,6 $\mu$	
										3,2 $\mu$	
										6,4 $\mu$	
Feed rate	f: 0,02 - 0,15	f: 0,03 - 0,15	f: 0,04 - 0,20	f: 0,05 - 0,25	f: 0,06 - 0,25	f: 0,06 - 0,25	f: 0,06 - 0,20	f: 0,06 - 0,20	Feed rate		
Depth of cut PBC-25S	$a_p$ : 0,04-0,25	$a_p$ : 0,04 - 0,3	$a_p$ : 0,06 - 0,4	$a_p$ : 0,06 - 0,4	$a_p$ : 0,08 - 0,4	$a_p$ : 0,08 - 0,4	$a_p$ : 0,1 - 0,4	$a_p$ : 0,12 - 0,4	Depth of cut PBC-25S		
Depth of cut PBC-25	$a_p$ : 0,02 - 0,25			$a_p$ : 0,05 - 0,4					Depth of cut PBC-25		
Cutting conditions	Continuous cut								Cutting conditions		

Application range for SBC-25C and SBC-25											
Hardturning, favoured in continuous Cut, $a_p = 0,04 - 6,0$ mm, HRc 48 - 65											
Vc: m/min	Cutting edge design (T-land + honing)								Ra ( $\mu$ )		
	A	B	C	D	E	F	G	H			
Cutting speed ↑ 350 300 250 200 150 100 50										0,1 $\mu$	Surface finish ↑
										0,2 $\mu$	
	Vc	Vc	Vc						Ra	0,4 $\mu$	
	Ra	Ra	Ra	Vc	Ra	Vc	Ra	Vc	Vc	0,8 $\mu$	
										1,6 $\mu$	
										3,2 $\mu$	
										6,4 $\mu$	
Feed rate	f: 0,02 - 0,20	f: 0,03 - 0,20	f: 0,03 - 0,20	f: 0,05 - 0,20	f: 0,06 - 0,25	f: 0,08 - 0,25	f: 0,08 - 0,25	f: 0,08 - 0,25	Feed rate		
Depth of cut SBC-25C	$a_p$ : 0,04 - 0,5	$a_p$ : 0,05 - 0,5	$a_p$ : 0,05 - 0,8	$a_p$ : 0,08 - 0,8	$a_p$ : 0,08 - 0,8	$a_p$ : 0,12 - 0,8	$a_p$ : 0,15 - 0,8	$a_p$ : 0,2 - 0,8	Depth of cut SBC-25C		
Depth of cut SBC-25	$a_p$ : 0,04 - 2,0					$a_p$ : 0,12 - 2,0			Depth of cut SBC-25		
Depth of cut SBC-25						$a_p$ : 0,25 - 6,0			Depth of cut SBC-25		
Cutting conditions	Continuous cut								Cutting conditions		



■ Cutting data Application range

**Application range for PBC-40S and PBC-40**  
Hardturning, favoured in interrupted cut, ap: 0,05 - 0,4 mm, HRc 48 - 65

Vc: m/min	Cutting edge design (T-land + honing)								Ra (μ)		
	A	B	C	D	E	F	G	H	Surface finish		
350										0,1μ	↑
300										0,2μ	
250	Vc									0,4μ	
200	Ra	Vc								0,8μ	
150		Ra	Vc							1,6μ	
100			Ra	Vc						3,2μ	
50										6,4μ	
Feed rate	f: 0,02 - 0,12	f: 0,03 - 0,15	f: 0,05 - 0,20	f: 0,06 - 0,20	f: 0,06 - 0,25	f: 0,06 - 0,25	f: 0,08 - 0,20	f: 0,08 - 0,20	Feed rate		
Depth of cut PBC-40S	ap: 0,05 - 0,25	ap: 0,06 - 0,3	ap: 0,08 - 0,3	ap: 0,08 - 0,3	ap: 0,10 - 0,4	ap: 0,10 - 0,4	ap: 0,15 - 0,4	ap: 0,20 - 0,4	Depth of cut PBC-40S		
Depth of cut PBC-40	ap: 0,04 - 0,25				ap: 0,07 - 0,4				Depth of cut PBC-40		
Cutting conditions	very slightly		slightly		medium		heavily		Cutting conditions	Interrupted cut	

**Application range for SBC-40C and SBC 40**  
Hardturning, favoured in interrupted Cut, ap = 0,05 - 6,0 mm, HRc 48 - 65

Vc: m/min	Cutting edge design (T-land + honing)								Ra (μ)		
	A	B	C	D	E	F	G	H	Surface finish		
350										0,1μ	↑
300										0,2μ	
250	Vc									0,4μ	
200		Vc								0,8μ	
150	Ra	Ra	Vc							1,6μ	
100			Ra	Vc						3,2μ	
50										6,4μ	
Feed rate	f: 0,02 - 0,20	f: 0,03 - 0,20	f: 0,03 - 0,20	f: 0,05 - 0,25	f: 0,06 - 0,25	f: 0,06 - 0,25	f: 0,06 - 0,25	f: 0,06 - 0,25	Feed rate		
Depth of cut SBC-40C	ap: 0,05 - 0,5	ap: 0,05 - 0,5	ap: 0,05 - 0,8	ap: 0,08 - 0,8	ap: 0,10 - 0,8	ap: 0,12 - 0,8	ap: 0,15 - 0,8	ap: 0,20 - 0,8	Depth of cut SBC-40C		
Depth of cut SBC-40	ap: 0,05 - 2,0						ap: 0,12 - 2,0		Depth of cut SBC-40		
Depth of cut SBC-40							ap: 0,25 - 6,0		Depth of cut SBC-40		
Cutting conditions	very slightly		slightly		medium		heavily		Cutting conditions	Interrupted cut	



cutting materials

ultrahard

## ■ ToolScout




In order for all users to exploit the full potential of our extremely high performance PcBN cutting materials, the following explanations and hints are of importance.

As shown in our previous catalogue supplement we offer our 6 coated PcBN-grades in up to 8 different chamfer geometries per cutting material as well as in various tipping options (see page 8). This large standard range enables us to meet basically all imaginable application profiles ex stock.

### Hard machining with PcBN

The cutting of hardened steel is generally referred to as hard machining. This cutting mechanism is a self-induced hot cutting process. This requires a defined and high temperature of about 550 to 750°C on the cutting zone. This necessary temperature is being produced by the transformation of existing energies into heat. This energy is released in the form of cutting speed  $V_c$ , feed rate  $f_n$ , depth of cut  $a_p$  as well as the chamfer geometries A-H of the PcBN cutting edges. Cooling is generally not required. Below we have illustrated 3 diagrams of hardness values. You can make out the decreasing hardness with the rising of the temperature. However significant differences are shown.

During the self-induced hot cutting process with our PcBN-grades the ideal hardness in the shear zone is at 40 to 45 HRc. This means that in such a case different cutting temperatures between 550°C up to 750°C are necessary.



At a temperature of approx. 600°C the steel grade 1.2379 still has a hardness of about 58 HRc, the steel grade 1.7131 about 48 HRc, and the steel grade 1.3505 only achieves about 36 HRc. The original hardness of each steel grade had been about 62 HRc.





In order to produce and maintain the ideal cutting temperature in the shear zone, it is obligatory to strictly stick to three particularities.

- the thermal conductivity of the PcBN-grade used (55% - 65% CBN)
- the applied chamfer geometry A-H, and also the positive top rake geometry (see page 13)
- as well as the hardness diagrams (hardness diagram with rising temperature)


In order to give you professional advice on our standard range for the intended application, the following checklist has to be strictly respected:

- precise specification of the steel grade and its hardness HRc
- the required surface finish Ra has to be determined as well as the depth of cut
- please decide if your cut is continuous to slightly-interrupted or medium to heavily-interrupted

Please select the PcBN grade as described on pages 6 and 7.


Becker	ISO	Composition	Application
SBC-25	BL	Uncoated solid PcBN-grade with low CBN content (65%), fine grit size (3 μ). Favoured application in continuous cut.	Hard turning, dry + wet HRc = 56 - 65 ap = 0.05 - 6 mm Ra = 0.2 - 3.2 μ
SBC-40	BL	Uncoated solid PcBN-grade with low CBN content (65%), super fine grit size (1 μ). For slightly- to heavily-interrupted cut	Hard turning, dry + wet HRc = 56 - 65 ap = 0.05 - 6 mm Ra = 0.2 - 3.2 μ

Now please choose the according chamfer geometry for the required surface finish, as shown in our diagrams on pages 16 and 17.



### Soft machining with PcBN

Soft machining encompasses the cutting of all materials in their natural hardness without any hardening process or similar applied. Thus the result means not any microstructural transformation has occurred. However it is absolutely necessary to keep materials in mind (super alloys, titanium etc.) that require a very high cutting temperature of 700 to 1,110°C, which can only be generated with the cutting material grade PcBN.



On pages 14 and 15 we have listed different application examples each explained by a simple diagram. On the left-hand side we have indicated the recommended cutting speed, and on the lower lines the according feed rate and depth of cut.

### Example:

100Cr6 – HRc 62  
ap= 0.25, fn = 0,1 mm  
interrupted cut  
required Ra = 0.6

**PcBN grade = PBC-40S**  
**chamfer "D" at Vc 160 m/min**  
**insert: CNGA 120408-D-40S-4SC**



ultrahard

cutting materials

# ISO-Insert Nomenclature

Order designation

**1 Basic shape**

**2 Clearance**

**3 Tolerance class**


**Tolerances in mm**

	m	s	d
A	0,005	0,025	0,025
F	0,005	0,025	0,013
C	0,013	0,025	0,025
H	0,013	0,025	0,013
E	0,005	0,025	0,025
G	0,025	0,130	0,025

	m	s	d <sup>1)</sup>	d <sup>1)</sup>
J	0,005	0,025	0,05	0,15
K	0,013	0,025	0,05	0,15
L	0,025	0,025	0,05	0,15
M <sup>1)</sup>	0,08	0,20	0,130	0,05
N <sup>1)</sup>	0,08	0,20	0,250	0,05
U <sup>1)</sup>	0,13	0,38	0,130	0,08

<sup>1)</sup> The exact tolerance is determined by size of insert.



**4 Insert type**

N	
F	
R	
A	
G	
M	
W	
T	
X	Special design

**5 Insert size**

If less than 10 use 0 in first place, decimals are omitted (Example: 9,525 mm = 09)

**6 Thickness in mm**

01 s = 1,59	
T1 s = 1,98	
02 s = 2,38	
03 s = 3,18	
T3 s = 3,97	
04 s = 4,76	
05 s = 5,56	
06 s = 6,35	

If less than 10 use 0 in first place, decimals are omitted (Example: 3,18 mm = 03)

ultrahard

cutting materials



TECHNOLOGY

TURNING

GROOVING

BORING

MILLING

**7** **Corner configuration**

**Radius**  
 02 = 0,2 mm  
 04 = 0,4 mm  
 08 = 0,8 mm  
 12 = 1,2 mm  
 16 = 1,6 mm  
 00 = round insert (inch)  
 M0 = round insert (metr.)

**10** **Solid-PcBN grades**

SBC-1 } Cast iron, sintered powered steel  
 SBC-10 }

SBC-25C } Hardtuning  
 SBC-25 }  
 SBC-40C }  
 SBC-40 }

**11** **Cutting edges**

Number of cutting edges:  
 2-8

**12** **Tipping variations**

**Solid PcBN grades**

EWS		PC-M	
MC-S		PC-M4	
PC-S		SBC	
PC-S4			

**7**  
**08**

**8**  
**W**

**9**  
**D**

**10**  
**15S**

**11**  
**4**

**12**  
**SC**

**8** **Wiper edge**

W = Wiper-edge, right + left hand  
 WR = Wiper-edge, right hand  
 WL = Wiper-edge, left hand

**9** **Cutting edge design**

Cutting edge design  
 T-land + honing

Conditions  
 A - H  
 see pages 14-17

**10** **Carbide Reinforced PcBN grades**

PBC-10S } Cast iron, sintered powered steel  
 PBC-10 }  
 PBC-15S }  
 PBC-15 }

PBC-25S } Hardtuning  
 PBC-25 }  
 PBC-40S }  
 PBC-40 }

**12** **Tipping variations**

**Carbide reinforced PcBN grades**


EW		MW		SE	
MC		GS			
SC		VM			



# TURNING | ISO

## CCGT

Standard tipped corners (positive)




EW

insert size	uncoated				coated																dimensions																	
	PBC-10		PBC-15		PBC-10S				PBC-15S				PBC-25S				PBC-40S																					
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>
060202-EW	●				●		●																														0,2	3,4
060204-EW	●				●		●																										6,35	2,8	2,38	6,45	0,4	3,1
060208-EW	●				●		●																														0,8	2,8
09T302-EW	●				●		●																														0,2	3,4
09T304-EW	●				●		●																										9,52	4,4	3,97	9,70	0,4	3,1
09T308-EW	●				●		●																														0,8	2,8

## CCGW

Standard tipped corners



GS

insert size	uncoated				coated																dimensions																	
	PBC-10		PBC-15		PBC-10S				PBC-15S				PBC-25S				PBC-40S																					
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	r	l <sub>1</sub>	
060204R/L-GS	●	●	●	●	●	●	●	●																													0,4	6,45
060208R/L-GS	●	●	●	●	●	●	●	●																									6,35	2,8	2,38		0,8	
09T304R/L-GS	●	●	●	●	●	●	●	●																													0,4	9,70
09T308R/L-GS	●	●	●	●	●	●	●	●																									9,52	4,4	3,97		0,8	







# TURNING | ISO

## ■ CNGA Standard tipped corners



EW



2MC



W-2MC

insert size	uncoated				coated																dimensions																									
	PBC-10		PBC-15		PBC-25		PBC-40		PBC-10S				PBC-15S				PBC-25S				PBC-40S																									
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>
120402-EW	●	●	●	●	●	●	●	●																																	12,70	5,13	4,76	12,90	0,2	3,4
120404-EW	●	●	●	●	●	●	●	●																																					0,4	3,1
120408-EW	●	●	●	●	●	●	●	●																																					0,8	2,8
120412-EW	●	●	●	●	●	●	●	●																																					1,2	2,5
120404-2MC	●	●	●	●	●	●	●	●																																					0,4	3,0
120408-2MC	●	●	●	●	●	●	●	●																																					0,8	2,7
120412-2MC	●	●	●	●	●	●	●	●																																					1,2	2,4
120402W-2MC	●	●	●	●	●	●	●	●																																					0,2	3,4
120404W-2MC	●	●	●	●	●	●	●	●																																					0,4	3,0
120408W-2MC	●	●	●	●	●	●	●	●																																					0,8	2,7

## ■ CNGA Sandwich tipped corners



2 SC



4 SC



W-4 SC

insert size	uncoated				coated																dimensions																																	
	PBC-10		PBC-15		PBC-25		PBC-40		PBC-10S				PBC-15S				PBC-25S				PBC-40S																																	
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>								
120404-2SC									●								●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●																	12,70	5,13	4,76	12,90	0,4	2,8
120408-2SC																																																					0,8	2,5
120412-2SC																																																					1,2	2,2
120404W-2SC									●								●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●																					0,4	2,8
120408W-2SC									●								●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●																					0,8	2,5
120404-4SC									●								●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●																					0,4	2,8
120408-4SC									●								●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●																					0,8	2,5
120412-4SC									●								●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●																					1,2	2,2
120404W-4SC									●								●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●																					0,4	2,8
120408W-4SC									●								●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●																					0,8	2,5



## CNGA

Double fullface



SE

insert size	uncoated				coated																dimensions																									
	PBC-10		PBC-15		PBC-25		PBC-40		PBC-10S				PBC-15S				PBC-25S				PBC-40S																									
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>
120408-SE									●	●							●	●	●						●	●	●						●	●	●	●	●	●	●	●	12,70	5,13	4,76	12,90	0,8	
120412-SE									●	●							●	●	●						●	●	●						●	●	●	●	●	●	●	●	12,70	5,13	4,76	12,90	1,2	

## CNGA

Solid tipped corners



PC-M



PC-M/4


insert size	uncoated				coated																dimensions									
	SBC-1		SBC-10		SBC-25		SBC-40		SBC-25C								SBC-40C													
	H	A	G	A	F	A	G	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>	
120404-PC-M	●		●		●		●																		12,70	5,13	4,76	12,90	0,4	2,8
120408-PC-M	●		●		●		●																		12,70	5,13	4,76	12,90	0,8	2,6
120412-PC-M	●		●		●		●																		12,70	5,13	4,76	12,90	1,2	2,4
120408-PC-M/4	●		●		●		●																		12,70	5,13	4,76	12,90	0,8	4,2

## CNGA

Solid tipped corners



2 MC/S



4 MC/S



W-4MC/S


insert size	uncoated				coated																dimensions									
	SBC-1		SBC-10		SBC-25		SBC-40		SBC-25C								SBC-40C													
	H	A	G	A	F	A	G	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>	
120404-2MC/S										●		●	●	●	●	●			●	●	●	●	●	●	12,70	5,13	4,76	12,90	0,4	2,8
120408-2MC/S										●		●	●	●	●	●			●	●	●	●	●	●	12,70	5,13	4,76	12,90	0,8	2,5
120412-2MC/S										●		●	●	●	●	●			●	●	●	●	●	●	12,70	5,13	4,76	12,90	1,2	2,2
120404W-2MC/S										●		●	●	●	●	●			●	●	●	●	●	●	12,70	5,13	4,76	12,90	0,4	2,8
120408W-2MC/S										●		●	●	●	●	●			●	●	●	●	●	●	12,70	5,13	4,76	12,90	0,8	2,5
120404-4MC/S										●		●	●	●	●	●			●	●	●	●	●	●	12,70	5,13	4,76	12,90	0,4	2,8
120408-4MC/S										●		●	●	●	●	●			●	●	●	●	●	●	12,70	5,13	4,76	12,90	0,8	2,6
120412-4MC/S										●		●	●	●	●	●			●	●	●	●	●	●	12,70	5,13	4,76	12,90	1,2	2,2
120404W-4MC/S										●		●	●	●	●	●			●	●	●	●	●	●	12,70	5,13	4,76	12,90	0,4	2,8
120408W-4MC/S										●		●	●	●	●	●			●	●	●	●	●	●	12,70	5,13	4,76	12,90	0,8	2,6



# TURNING | ISO

## CPGW

Standard tipped corners




GS

insert size	uncoated				coated																dimensions																	
	PBC-10		PBC-15		PBC-10S				PBC-15S				PBC-25S				PBC-40S																					
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>
050204R/L-GS	●	●	●	●	●	●	●	●																									5,56	2,50	2,38		0,4	5,6
060204R/L-GS	●	●	●	●	●	●	●	●																									6,35	2,80	2,38		0,4	6,5
060208R/L-GS	●	●	●	●	●	●	●	●																													0,8	6,5

## CPGT

Standard tipped corners (positive)




EW

insert size	uncoated				coated																dimensions																	
	PBC-10		PBC-15		PBC-10S				PBC-15S				PBC-25S				PBC-40S																					
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>
04T102-EW	●				●	●	●	●																									4,76	2,10	1,98	4,80	0,2	2,2
04T104-EW	●				●	●	●	●																													0,4	2,0
05T102-EW	●				●	●	●	●																									5,56	2,50	1,98	5,60	0,2	2,4
05T104-EW	●				●	●	●	●																													0,4	2,2
050202-EW	●	●			●	●	●	●																									5,56	2,50	2,38	5,60	0,2	2,4
050204-EW	●	●			●	●	●	●																													0,4	2,2
060202-EW	●	●			●	●	●	●																									6,35	2,80	2,38	6,45	0,4	3,4
060208-EW	●	●			●	●	●	●																													0,8	2,8

## CPGW

Standard tipped corners




EW

insert size	uncoated				coated																dimensions																	
	PBC-10		PBC-15		PBC-10S				PBC-15S				PBC-25S				PBC-40S																					
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>
04T102-EW	●	●	●	●	●	●	●	●																									4,76	2,10	1,98	4,80	0,2	2,2
04T104-EW	●	●	●	●	●	●	●	●																													0,4	2,0
05T102-EW	●	●	●	●	●	●	●	●																									5,56	2,50	1,98	5,60	0,2	2,4
05T104-EW	●	●	●	●	●	●	●	●																													0,4	2,2
050202-EW	●	●	●	●	●	●	●	●																									5,56	2,50	2,38	5,60	0,2	2,4
050204-EW	●	●	●	●	●	●	●	●																													0,4	2,2
060202-EW	●	●	●	●	●	●	●	●																									6,35	2,80	2,38	6,45	0,2	3,4
060208-EW	●	●	●	●	●	●	●	●																													0,8	2,8



## DCGT

Standard tipped corners (positive)




EW


insert size	uncoated				coated																dimensions																	
	PBC-10		PBC-15		PBC-10S				PBC-15S				PBC-25S				PBC-40S																					
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>
070202-EW	●	●	●	●																													6,35	2,80	2,38	7,75	0,2	3,9
070204-EW	●	●	●	●																																	0,4	3,5
070208-EW	●	●	●	●																																	0,8	3,0
11T302-EW	●	●	●	●																													9,52	4,40	3,97	11,60	0,2	3,9
11T304-EW	●	●	●	●																																	0,4	3,5
11T308-EW	●	●	●	●																																	0,8	3,0

## DCGW

Standard tipped corners



EW



2MC

insert size	uncoated				coated																dimensions																	
	PBC-10		PBC-15		PBC-10S				PBC-15S				PBC-25S				PBC-40S																					
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>
070202-EW	●	●	●	●																													6,35	2,80	2,38	7,75	0,2	3,9
070204-EW	●	●	●	●																																	0,4	3,5
070208-EW	●	●	●	●																																	0,8	3,0
070202-2MC	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●					0,2	3,9
070204-2MC	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●					0,4	3,5
070208-2MC	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●					0,8	3,0
11T302-EW	●	●	●	●																													9,52	4,40	3,97	11,60	0,2	3,9
11T304-EW	●	●	●	●																																	0,4	3,5
11T308-EW	●	●	●	●																																	0,8	3,0
11T302-2MC	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●					0,2	3,9
11T304-2MC	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●					0,4	3,5
11T308-2MC	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●					0,8	3,0
150404-EW	●	●	●	●																													12,70	5,50	4,76	15,50	0,4	3,5
150408-EW	●	●	●	●																																	0,8	3,0



# TURNING | ISO

TECHNOLOGY


TURNING

GROOVING


BORING

MILLING


## DCGW Solid tipped corners



EWS



W-EWS



2MC/S

insert size	uncoated								coated																dimensions									
	SBC1			SBC10			SBC25		SBC40				SBC-25C								SBC-40C													
	H	A	G	A	F	A	G	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>					
070202-EWS		●	●	●	●	●	●																	6,35	2,80	2,38	7,75			0,2	3,9			
070204-EWS		●	●	●	●	●	●																									0,4	3,5	
070208-EWS		●	●	●	●	●	●																									0,8	3,0	
070201R/L-W-EWS		●	●	●	●	●	●																									0,1	3,0	
070202R/L-W-EWS		●	●	●	●	●	●																									0,2	3,0	
070204R/L-W-EWS		●	●	●	●	●	●																									0,4	3,0	
070202-2MC/S								●	●		●	●		●	●	●		●			●		●					0,2	3,4					
070204-2MC/S								●	●		●	●		●	●	●		●			●	●	●					0,4	3,0					
070208-2MC/S								●			●	●	●		●	●		●		●	●	●	●					0,8	2,6					
11T301R/L-W-EWS		●	●	●	●	●	●																	9,52	4,40	3,97	11,60			0,1	3,0			
11T302R/L-W-EWS		●	●	●	●	●	●																								0,2	3,0		
11T304R/L-W-EWS		●	●	●	●	●	●																								0,4	3,0		
11T308R/L-W-EWS		●	●	●	●	●	●																								0,8	3,0		
11T302-2MC/S								●	●	●		●	●		●	●	●	●		●	●	●									0,2	3,4		
11T304-2MC/S									●		●	●	●	●	●	●		●	●	●	●	●									0,4	3,0		
11T308-2MC/S								●		●	●	●	●	●	●	●	●		●	●	●	●					0,8	2,6						






## DNGA


Standard tipped corners  
Sandwich tipped corners




EW



MW



2SC



4SC

insert size	uncoated				coated																dimensions																									
	PBC-10		PBC-15		PBC-25S				PBC-40S				PBC-10S				PBC-15S				PBC-25S				PBC-40S																					
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>
110402-EW	●	●	●	●	●	●	●	●																																					0,2	3,9
110404-EW	●	●	●	●	●	●	●	●																																	9,52	3,81	4,76	11,60	0,4	3,5
110408-EW	●	●	●	●	●	●	●	●																																					0,8	3,0
150402-EW	●	●	●	●	●	●	●	●																																					0,2	3,9
150404-EW	●	●	●	●	●	●	●	●																																					0,4	3,5
150408-EW	●	●	●	●	●	●	●	●																																					0,8	3,0
150408-MW	●	●	●	●	●	●	●	●																																					0,8	5,0
150412-MW	●	●	●	●	●	●	●	●																																	12,70	5,13	4,76	15,50	1,2	4,5
150404-2SC									●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●													0,4	2,8
150408-2SC									●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●													0,8	2,6
150404-4SC									●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●													0,4	2,8
150408-4SC									●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●													0,8	2,6
150604-EW	●	●	●	●	●	●	●	●																																					0,4	3,5
150608-EW	●	●	●	●	●	●	●	●																																					0,8	3,0
150604-MW	●	●	●	●	●	●	●	●																																					0,4	5,5
150608-MW	●	●	●	●	●	●	●	●																																					0,8	5,0
150612-MW	●	●	●	●	●	●	●	●																																	12,70	5,13	6,35	15,50	1,2	4,5
150604-2SC									●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●													0,4	2,8	
150608-2SC									●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●													0,8	2,6	
150604-4SC									●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●													0,4	2,8	
150608-4SC									●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●													0,8	2,6	



# TURNING | ISO

TECHNOLOGY

TURNING

GROOVING

BORING


MILLING

## ■ DNGA


Solid tipped corners



PC-S



PC-S/4




PC-M


insert size	uncoated								coated																dimensions					
	SBC1		SBC10		SBC25		SBC40		SBC-25C								SBC-40C													
	H	A	G	A	F	A	G	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>	
150404-PC-S	●	●	●	●	●	●	●																	12,70	5,13	4,76	15,50	0,4	2,8	
150408-PC-S	●	●	●	●	●	●	●																					0,8	2,6	
150412-PC-S	●	●	●	●	●	●	●																					1,2	2,4	
150404-PC-M	●		●		●		●																					0,4	2,8	
150408-PC-M	●		●		●		●																					0,8	2,6	
150412-PC-M	●		●		●		●																					1,2	2,4	
150604-PC-S	●	●	●	●	●	●	●																					0,4	2,8	
150608-PC-S	●	●	●	●	●	●	●																					0,8	2,6	
150612-PC-S	●	●	●	●	●	●	●																					1,2	2,4	
150604-PC-S/4	●																										0,4	4,0		
150608-PC-S/4	●																											0,8	3,6	
150612-PC-S/4	●																											1,2	3,2	
150604-PC-M	●		●		●		●																					0,4	2,8	
150608-PC-M	●		●		●		●																					0,8	2,6	
150612-PC-M	●		●		●		●																					1,2	2,4	

## ■ DNGA

Solid tipped corners



2MC/S



4MC/S

insert size	uncoated								coated																dimensions					
	SBC1		SBC10		SBC25		SBC40		SBC-25C								SBC-40C													
	H	A	G	A	F	A	G	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>	
150604-2MC/S								●		●	●	●	●	●	●			●	●	●	●	●	●		12,70	5,13	6,35	15,50	0,4	2,8
150608-2MC/S								●		●	●	●	●	●	●			●	●	●	●	●	●						0,8	2,5
150612-2MC/S								●		●	●	●	●	●	●			●	●	●	●	●	●						1,2	2,2
150604-4MC/S								●		●	●	●	●	●	●			●	●	●	●	●	●					0,4	2,8	
150608-4MC/S								●		●	●	●	●	●	●			●	●	●	●	●	●					0,8	2,5	
150612-4MC/S								●		●	●	●	●	●	●			●	●	●	●	●	●					1,2	2,2	



## RCGW

Fullface



VM

insert size	uncoated				coated																												dimensions												
	PBC-10		PBC-15		PBC-25		PBC-40		PBC-10S							PBC-15S							PBC-25S							PBC-40S							d		s	l		r	l <sub>1</sub>		
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r
0602M0-VM	●	●			●	●	●	●																																6,00	2,80	2,38			
0803M0-VM	●	●			●	●	●	●																																8,00	3,40	3,18			
1003M0-VM		●				●		●																																10,00	4,40	3,18			
10T3M0-VM		●				●		●																																12,00	4,40	3,97			
1204M0-VM		●				●		●																																12,00	4,40	4,76			

## RCGX

Fullface



VM

insert size	uncoated				coated																												dimensions												
	PBC-10		PBC-15		PBC-25		PBC-40		PBC-10S							PBC-15S							PBC-25S							PBC-40S							d		d <sub>1</sub>	s	l		r	l <sub>1</sub>	
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r
060600-VM			●	●	●	●	●	●																																6,35		6,35			
090700-VM			●	●	●	●	●	●																																9,52		7,94			
120700-VM			●	●	●	●	●	●																																12,70		7,94			

## RNGA

Fullface  
Double fullface



VM



SE

insert size	uncoated				coated																												dimensions																						
	PBC-10		PBC-15		PBC-25		PBC-40		PBC-10S							PBC-15S							PBC-25S							PBC-40S							d		d <sub>1</sub>	s	l		r	l <sub>1</sub>											
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>									
090300-VM	●	●			●	●																																		9,52	3,81	3,18													
120400-VM	●	●			●	●																																		12,70	5,13	4,76													
120400-SE									●	●	●					●	●	●	●					●	●	●																													



# TURNING | ISO

TECHNOLOGY

TURNING

## RNGN

Fullface  
Double fullface



VM



SE

insert size	uncoated				coated																dimensions																																												
	PBC-10		PBC-15		PBC-25		PBC-10S				PBC-15S				PBC-25S				PBC-40S																																														
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>																			
090300-VM	●	●			●	●	●	●									●	●	●	●	●	●	●											9,52		3,18																													
090300-SE									●	●	●						●	●	●	●	●	●	●											12,70		3,18																													
120300-SE									●	●	●						●	●	●	●	●	●	●											12,70		3,18																													
120400-VM	●	●			●	●	●	●																										12,70		4,76																													
120400-SE									●	●	●						●	●	●	●	●	●	●																																										

## RNGN

Solid




SBC

insert size	uncoated				coated																dimensions																																			
	SBC1		SBC10		SBC25		SBC-25C				SBC-40C																																													
	H	A	G		A	F	A	G	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>																										
090300-SBC	●		●		●	●		●																									9,52		3,18																					
120300-SBC	●		●		●	●		●																									12,70		3,18																					
120400-SBC	●		●		●	●		●																									12,70		4,76																					

GROOVING

## SCGW

Standard tipped corners



EW



GS

insert size	uncoated				coated																dimensions																												
	PBC-10		PBC-15		PBC-25		PBC-10S				PBC-15S				PBC-25S				PBC-40S																														
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>			
09T304-EW	●	●	●	●	●	●	●	●																										9,52	4,40	3,97	9,52			0,4	3,5								
09T308-EW	●	●	●	●	●	●	●	●																																0,8	3,4								
09T304-GS	●	●	●	●	●	●	●	●																																0,4	9,5								
09T308-GS	●	●	●	●	●	●	●	●																																0,8	9,5								
120404-EW	●	●			●	●	●	●																									12,70	5,50	4,76	12,70			0,4	3,5									
120408-EW	●	●			●	●	●	●																															0,8	3,4									
120412-EW	●	●			●	●	●	●																															1,2	3,2									

BORING

MILLING



## SNGN

Solid tipped corners



PC-M

insert size	uncoated				coated																dimensions														
	SBC1		SBC10		SBC25		SBC40		SBC-25C								SBC-40C																		
	H	A	G	A	F	A	G	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>						
090304-PC-M	●				●		●																							9,52		3,18	9,52	0,4	3,0
090308-PC-M	●				●		●																							9,52		3,18	9,52	0,8	2,8
090312-PC-M	●				●		●																							9,52		3,18	9,52	1,2	2,6
120404-PC-M	●	●	●		●		●																							12,70		4,76	12,70	0,4	3,0
120408-PC-M	●	●	●		●		●																							12,70		4,76	12,70	0,8	2,8
120412-PC-M	●	●	●		●		●																							12,70		4,76	12,70	1,2	2,6

## SNGN

Sandwich tipped corners  
Double fullface



SE



8 SC

insert size	uncoated				coated																dimensions																								
	PBC-10		PBC-15		PBC-25		PBC-40		PC-10S				PBC-15S				PBC-25S				PBC-40S																								
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r
090308-SE									●	●	●																				9,52		3,18	9,52	0,8										
120308-SE									●	●	●																				12,70		3,18	12,70	0,8										
120408-8SC									●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	12,70		4,76	12,70	0,8	2,8									
120412-8SC									●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	12,70		4,76	12,70	1,2	2,6									
120408-SE									●	●	●																			12,70		4,76	12,70	0,8											
120412-SE									●	●	●																			12,70		4,76	12,70	1,2											

## SNGN

Solid



SBC

insert size	uncoated				coated																dimensions														
	SBC1		SBC10		SBC25		SBC40		SBC-25C								SBC-40C																		
	H	A	G	A	F	A	G	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>						
090304-SBC	●		●		●		●																							9,52		3,18		0,4	9,5
090308-SBC	●		●		●		●																							9,52		3,18		0,8	9,5
090312-SBC	●		●		●		●																							9,52		3,18		1,2	9,5







# TURNING | ISO

## ■ SNGA

Standard/Sandwich tipped corners  
Double fullface



EW



8-SC




SE

insert size	uncoated				coated																dimensions																									
	PBC-10		PBC-15		PBC-25				PBC-40				PBC-10S				PBC-15S				PBC-25S				PBC-40S																					
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D		E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r
120404-EW	●	●	●	●	●	●	●	●																																					0,4	3,5
120408-EW	●	●	●	●	●	●	●	●																													0,8	3,4								
120412-EW	●	●	●	●	●	●	●	●																													1,2	3,2								
120408-8SC									●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	12,70	5,13	4,76	12,70	0,8	2,8								
120412-8SC									●		●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●					1,2	2,6									
120408-SE									●	●	●					●	●	●	●					●	●	●	●	●	●	●	●					0,8										
120412-SE									●	●	●					●	●	●	●					●	●	●	●	●	●	●	●					1,2										

## ■ SNGA

Solid tipped corners



PC-S



PC-M

insert size	uncoated				coated																dimensions																	
	SBC1		SBC10		SBC25				SBC40				SBC-25C								SBC-40C																	
	H	A	G	A	F	A	G	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E		F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>
120404-PC-S	●	●	●	●	●	●	●	●																													0,4	3,0
120408-PC-S	●	●	●	●	●	●	●	●																													0,8	2,8
120412-PC-S	●	●	●	●	●	●	●	●																													1,2	2,6
120404-PC-M	●		●		●		●																										12,70	5,13	4,76	12,70	0,4	3,0
120408-PC-M	●		●		●		●																														0,8	2,8
120412-PC-M	●		●		●		●																														1,2	2,6



## SPGN

Standard tipped corners



EW

insert size	uncoated				coated																dimensions																	
	PBC-10	PBC-15	PBC-25	PBC-40	PBC-10S				PBC-15S				PBC-25S				PBC-40S						d	d <sub>1</sub>	s	l	r	l <sub>1</sub>										
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F							G	H	A	B	C	D	E	F	G	H
120308-EW	●	●	●																														12,70		3,18	12,70	0,8	3,4
120312-EW	●	●		●																																	1,2	3,2

## SPGW

Standard tipped corners



EW



GS

insert size	uncoated				coated																dimensions																	
	PBC-10	PBC-15	PBC-25	PBC-40	PBC-10S				PBC-15S				PBC-25S				PBC-40S						d	d <sub>1</sub>	s	l	r	l <sub>1</sub>										
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F							G	H	A	B	C	D	E	F	G	H
09T304-EW	●	●		●																																	0,4	3,5
09T308-EW	●	●	●																														9,52	4,40	3,97	9,52	0,8	3,4
09T304-GS	●	●		●																																	0,4	9,5
09T308-GS	●	●	●																																		0,8	9,5
120404-EW	●	●		●																																	0,4	3,5
120408-EW	●	●	●																														12,70	5,50	4,76	12,70	0,8	3,4
120412-EW	●	●		●																																	1,2	3,2

## TBGN

Fullface



VM

insert size	uncoated				coated																dimensions																	
	PBC-10	PBC-15	PBC-25	PBC-40	PBC-10S				PBC-15S				PBC-25S				PBC-40S						d	d <sub>1</sub>	s	l	r	l <sub>1</sub>										
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F							G	H	A	B	C	D	E	F	G	H
060102-VM	●	●		●																																	0,2	6,5
060104-VM	●	●		●																													3,97		1,58		0,4	6,5
060108-VM	●	●		●																																	0,8	6,5



# TURNING | ISO

## TBGW

Fullface




VM

insert size	uncoated				coated																dimensions																																	
	PBC-10		PBC-15		PBC-25				PBC-40				PBC-10S				PBC-15S				PBC-25S				PBC-40S																													
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>								
060102-VM	●	●			●	●	●	●																																									3,97	2,30	1,58		0,2	6,5
060104-VM	●	●			●	●	●	●																																					0,4	6,5								
060108-VM	●	●			●	●	●	●																																					0,8	6,5								

## TCGT

Standard tipped corners (positive)



EW


insert size	uncoated				coated																dimensions																									
	PBC-10		PBC-15		PBC-25				PBC-40				PBC-10S				PBC-15S				PBC-25S				PBC-40S																					
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>
090202-EW	●	●			●	●	●	●																																	5,56	2,50	2,38	9,60	0,2	3,8
090204-EW	●	●			●	●	●	●																																					0,4	3,5
110202-EW	●	●			●	●	●	●																																	6,35	2,80	2,38	11,00	0,2	3,8
110204-EW	●	●			●	●	●	●																																					0,4	3,5

# TURNING ISO




## TCGW


Standard tipped corners



EW



3 MC




GS

insert size	uncoated				coated																dimensions																																		
	PBC-10		PBC-15		PBC-25				PBC-40				PBC-10S				PBC-15S				PBC-25S				PBC-40S																														
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>									
090202-EW	●	●			●	●	●	●																																						0,2	3,8								
090204-EW	●	●	●	●	●	●	●	●																																						0,4	3,5								
090208-EW	●	●			●	●	●	●																																						0,8	3,0								
090202-3MC								●	●	●	●																																							5,56	2,50	2,38	9,60	0,2	2,6
090204-3MC								●	●	●	●	●	●	●	●	●																																			0,4	2,2			
090208-3MC								●	●	●	●	●	●	●																																				0,8	1,8				
090204-GS	●	●			●	●	●	●																																										0,4	9,6				
110202-EW	●	●			●	●	●	●																																										0,2	3,8				
110204-EW	●	●	●	●	●	●	●	●																																										0,4	3,5				
110208-EW	●	●			●	●	●	●																																										0,8	3,0				
110202-3MC								●	●	●	●																																										0,2	2,9	
110204-3MC								●	●	●	●	●	●	●	●	●																																				0,4	2,5		
110208-3MC								●	●	●	●	●	●	●	●																																					0,8	2,1		
110204-GS	●	●			●	●	●	●																																											0,4	11,0			
110208-GS	●	●			●	●	●	●																																										0,8	11,0				
16T304-3MC								●	●	●	●																																								0,4	3,2			
16T308-3MC								●	●	●	●	●	●	●	●	●																																			0,8	2,7			
16T304-GS	●	●			●	●	●	●																																											0,4	16,5			
16T308-GS	●	●			●	●	●	●																																										0,8	16,5				

## TNGN

Solid tipped corners



PC-M

insert size	uncoated				coated																dimensions																																	
	SBC1		SBC10		SBC25				SBC40				SBC-25C								SBC-40C																																	
	H	A	G		A	F	A	G	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>																								
160404-PC-M	●				●		●																																													0,4	3,0	
160408-PC-M	●				●		●																																													0,8	2,6	
160412-PC-M	●				●		●																																														1,2	2,4



# TURNING | ISO

## ■ TNGN

Solid



SBC

insert size	uncoated								coated																dimensions											
	SBC1		SBC10		SBC25		SBC40		SBC-25C								SBC-40C																			
	H	A	G	A	F	A	G	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>							
110304-SBC	●		●		●		●																												0,4	
110308-SBC	●		●		●		●																												0,8	
110312-SBC	●		●		●		●																												1,2	

## ■ TNGN

Double fullface



SE


insert size	uncoated								coated																dimensions																				
	PBC-10		PBC-15		PBC-25		PBC-40		PBC-10S				PBC-15S				PBC-25S				PBC-40S																								
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r
110304-SE								●	●	●																										0,4									
110308-SE								●	●	●																											0,8								
160404-SE								●	●	●																										0,4									
160408-SE								●	●	●																										0,8									
160412-SE								●	●	●																										1,2									

## ■ TNGA


Standard-/ Sandwich tipped corners  
Double fullface



EW



6 SC



SE

insert size	uncoated								coated																dimensions																				
	PBC-10		PBC-15		PBC-25		PBC-40		PBC-10S				PBC-15S				PBC-25S				PBC-40S																								
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r
110304-EW	●	●			●	●	●	●																												0,4	2,8								
110308-EW	●	●			●	●	●	●																												0,8	2,5								
110304-SE								●	●	●																										0,4									
110308-SE								●	●	●																											0,8								
160404-EW	●	●			●	●	●	●																												0,4	3,5								
160408-EW	●	●			●	●	●	●																												0,8	3,0								
160412-EW	●	●			●	●	●	●																												1,2	2,6								
160404-6SC								●			●	●	●	●																						0,4	2,8								
160408-6SC								●	●	●	●	●	●	●																						0,8	2,5								
160412-6SC								●			●	●	●	●																						1,2	2,2								
160404-SE								●	●	●																										0,4									
160408-SE								●	●	●																										0,8									
160412-SE								●	●	●																										1,2									



# TURNING ISO




## TNGA

Solid tipped corners



PC-S



PC-M



PC-M/4


insert size	uncoated								coated																dimensions					
	SBC1		SBC10		SBC25		SBC40		SBC-25C								SBC-40C													
	H	A	G	A	F	A	G	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>	
160404-PC-S	●	●	●	●	●	●	●																						0,4	3,0
160408-PC-S	●	●	●	●	●	●	●																						0,8	2,6
160412-PC-S	●	●	●	●	●	●	●																						1,2	2,4
160404-PC-M	●		●		●		●																						0,4	3,0
160408-PC-M	●		●		●		●																						0,8	2,6
160412-PC-M	●		●		●		●																						1,2	2,4
160404-PC-M/4	●																												0,4	4,5
160408-PC-M/4	●																												0,8	4,2
160412-PC-M/4	●																												1,2	4,0

## TNGA

Solid tipped corners



3MC/S




6MC/S

insert size	uncoated								coated																dimensions					
	SBC1		SBC10		SBC25		SBC40		SBC-25C								SBC-40C													
	H	A	G	A	F	A	G	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>	
160404-3MC/S								●	●		●	●	●				●	●	●	●	●	●							0,4	3,0
160408-3MC/S								●	●	●	●	●	●	●			●	●	●	●	●	●	●						0,8	2,6
160412-3MC/S								●	●		●	●	●	●			●	●	●	●	●	●	●						1,2	2,4
160404-6MC/S								●	●		●	●	●			●	●	●	●	●	●	●							0,4	3,0
160408-6MC/S								●	●	●	●	●	●	●			●	●	●	●	●	●	●						0,8	2,6
160412-6MC/S								●	●		●	●	●	●			●	●	●	●	●	●	●						1,2	2,4

## TPGA

Standard tipped corners



EW


insert size	uncoated				coated																								dimensions																					
	PBC-10		PBC-15		PBC-25		PBC-40		PBC-10S						PBC-15S						PBC-25S						PBC-40S																							
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>				
110302-EW	●				●		●																																									0,2	3,8	
110304-EW	●	●	●	●	●	●	●																																										0,4	3,5
110308-EW	●				●		●																																										0,8	3,0




# TURNING | ISO

## TPGN

Standard tipped corners



EW



GS




VM


insert size	uncoated				coated																dimensions																									
	PBC-10		PBC-15		PBC-25				PBC-40				PBC-10S				PBC-15S				PBC-25S				PBC-40S																					
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>
110302-EW	●	●			●	●	●	●																																	6,35		3,18	11,00	0,2	3,8
110304-EW	●	●	●	●	●	●	●	●																																					0,4	3,5
110308-EW	●	●			●	●	●	●																																					0,8	3,0
110304-GS		●			●		●	●																																	6,35		3,18	11,00	0,4	11,0
110308-GS		●			●		●	●																																					0,8	11,0
110304-VM		●		●	●		●	●																																					0,4	11,0
110308-VM		●			●		●	●																																					0,8	11,0
160304-EW	●	●			●	●	●	●																																	9,52		3,18	16,50	0,4	3,5
160308-EW	●	●			●	●	●	●																																					0,8	3,0
160304-GS		●			●		●	●																																	9,52		3,18	16,50	0,8	16,5
160308-GS		●			●		●	●																																	9,52		3,18	16,50	0,8	16,5

## TPGW

Standard tipped corners



EW



GS

insert size	uncoated				coated																dimensions																									
	PBC-10		PBC-15		PBC-25				PBC-40				PBC-10S				PBC-15S				PBC-25S				PBC-40S																					
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>
090202-EW		●			●		●	●																																	5,56	2,50	2,38	9,60	0,2	3,8
090204-EW	●	●			●		●	●																																	5,56	2,50	2,38	9,60	0,4	3,5
090204-GS		●			●		●	●																																	5,56	2,50	2,38	9,60	0,4	9,6
110202-EW		●			●		●	●																																	6,35	2,80	2,38	11,00	0,2	3,8
110204-EW	●	●			●		●	●																																	6,35	2,80	2,38	11,00	0,4	3,5
110208-GS		●			●		●	●																																	6,35	2,80	2,38	11,00	0,8	11,0
110302-EW	●	●			●		●	●																																	6,35	2,80	3,18	11,00	0,2	3,8
110304-EW	●	●			●		●	●																																	6,35	2,80	3,18	11,00	0,4	3,5
110308-EW	●	●			●		●	●																																	6,35	2,80	3,18	11,00	0,8	3,0
110304-GS	●	●			●		●	●																																	6,35	2,80	3,18	11,00	0,4	11,0
110308-GS	●	●			●		●	●																																	6,35	2,80	3,18	11,00	0,8	11,0
160304-EW	●	●			●		●	●																																	9,52	4,40	4,76	16,50	0,4	3,5
160308-EW	●	●			●		●	●																																	9,52	4,40	4,76	16,50	0,8	3,0
160308-GS		●			●		●	●																																	9,52	4,40	4,76	16,50	0,8	16,5



## VBGW


Solid tipped corners



EWS



2MC-S




2MC-S/4

insert size	uncoated								coated																dimensions					
	SBC1		SBC10		SBC25		SBC40		SBC-25C								SBC-40C													
	H	A	G	A	F	A	G	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>	
110202-EWS		●	●	●	●	●	●																6,50	2,90	2,38	11,10	0,2	3,5		
110204-EWS		●	●	●	●	●	●																				0,4	3,1		
160402-EWS		●	●	●	●	●	●																				0,2	3,5		
160404-EWS		●	●	●	●	●	●																				0,4	3,1		
160408-EWS		●	●	●	●	●	●																				0,8	2,8		
160402-2MC-S		●	●	●	●	●	●																				0,2	3,5		
160404-2MC-S		●	●	●	●	●	●																				0,4	3,1		
160408-2MC-S		●	●	●	●	●	●																				0,8	2,8		
160404-2MC-S/4	●																										0,4	4,4		
160408-2MC-S/4	●																										0,8	4,2		
160412-2MC-S/4	●																										1,2	4,0		

## VBGW

Standard tipped corners



MW



2MC


insert size	uncoated				coated																dimensions																		
	PBC-10		PBC-15		PBC-25		PBC-40		PBC-10S				PBC-15S				PBC-25S				PBC-40S																		
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>	
110202-MW	●	●	●	●	●	●	●																														0,2	4,7	
110204-MW	●	●	●	●	●	●	●																															0,4	4,5
110208-MW	●	●			●	●	●																														0,8	4,2	
160402-MW	●	●			●	●	●																														0,2	5,3	
160404-MW	●	●	●	●	●	●	●																														0,4	5,0	
160408-MW	●	●			●	●	●																														0,8	4,4	
160412-MW	●	●			●	●	●																														1,2	3,9	
160416-MW	●				●	●	●																														1,6	3,5	
160404-2MC								●	●	●	●			●	●	●	●			●	●	●	●			●	●	●	●	●	●	●	●	●	●	●	0,4	3,1	
160408-2MC								●	●	●	●			●	●	●	●			●	●	●	●			●	●	●	●	●	●	●	●	●	●	●	0,8	2,5	



# TURNING | ISO

## VCGT

Solid tipped corners (positive)




EWS


insert size	uncoated								coated																dimensions					
	SBC1		SBC10		SBC25		SBC40		SBC-25C								SBC-40C													
	H	A	G	A	F	A	G	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>	
070202-EWS		●		●		●																		3,97	2,20	2,38	6,90	0,2	3,5	
070204-EWS		●		●		●																						0,4	3,2	
110202-EWS		●		●		●																			6,35	2,90	3,18	11,10	0,2	3,5
110204-EWS		●		●		●																						0,4	3,2	
130302-EWS		●		●		●																			7,94	3,40	3,18	13,30	0,2	3,5
130304-EWS		●		●		●																						0,4	3,2	
160402-EWS		●		●		●																						0,2	3,5	
160404-EWS		●		●		●																			9,52	4,40	4,76	16,60	0,4	3,2
160408-EWS		●		●		●																						0,8	2,8	

## VCGW


Solid tipped corners



EWS



2MC-S




2MC-S/4

insert size	uncoated								coated																dimensions					
	SBC1		SBC10		SBC25		SBC40		SBC-25C								SBC-40C													
	H	A	G	A	F	A	G	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>	
070202-EWS		●	●	●	●	●																			3,97	2,20	2,38	6,90	0,2	3,5
070204-EWS		●	●	●	●	●																							0,4	3,2
110302-MC-S		●	●	●	●	●																			6,35	2,90	3,18	11,10	0,2	3,5
110304-MC-S		●	●	●	●	●																							0,4	3,2
130302-EWS		●	●	●	●	●																			7,94	3,40	3,18	13,30	0,2	3,5
130304-EWS		●	●	●	●	●																						0,4	3,2	
160402-EWS		●	●	●	●	●																						0,2	3,5	
160404-EWS		●	●	●	●	●																			9,52	4,40	4,76	16,60	0,4	3,2
160408-EWS		●	●	●	●	●																						0,8	2,8	
160402-2MC-S		●	●	●	●	●																						0,2	3,5	
160404-2MC-S		●	●	●	●	●																			9,52	4,40	4,76	16,60	0,4	3,2
160408-2MC-S		●	●	●	●	●																						0,8	2,8	
160404-2MC-S/4	●																											0,4	4,4	
160408-2MC-S/4	●																											0,8	4,2	
160412-2MC-S/4	●																											1,2	4,0	



## VCGW


Standard tipped corners



insert size	uncoated				coated																dimensions																								
	PBC-10		PBC-15		PBC-25				PBC-40				PBC-10S				PBC-15S				PBC-25S				PBC-40S				d		d <sub>1</sub>	s	l	r	l <sub>1</sub>										
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r
070202-MW	●	●	●	●	●	●	●	●																																3,97	2,20	2,38	6,90	0,2	3,8
070204-MW	●	●	●	●	●	●	●	●																																				0,4	3,5
110302-MW	●	●	●	●	●	●	●	●																																				0,2	4,7
110304-MW	●	●	●	●	●	●	●	●																																				0,4	4,5
110308-MW	●	●			●	●	●	●																								6,35	2,90	3,18	11,00	0,8	4,2								
110304-2MC					●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●									0,4	3,1			0,8	2,5
110308-2MC					●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●									0,4	3,1			0,8	2,5
160402-MW	●	●	●	●	●	●	●	●																																0,2	5,3			0,4	5,5
160404-MW	●	●	●	●	●	●	●	●																																				0,8	4,4
160408-MW	●	●	●	●	●	●	●	●																																				1,2	3,9
160412-MW	●	●	●	●	●	●	●	●																																				0,4	3,1
160404-2MC					●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●									0,4	3,1			0,8	2,5
160408-2MC					●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●									0,8	2,5				

## VNGA

Solid tipped corners



insert size	uncoated				coated																dimensions																				
	SBC1		SBC10		SBC25				SBC40				SBC-25C								SBC-40C								d		d <sub>1</sub>	s	l	r	l <sub>1</sub>						
	H	A	G		A	F	A	G	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>											
160402-PC-S	●	●	●		●	●	●	●																																0,2	3,0
160404-PC-S	●	●	●		●	●	●	●																																0,4	2,8
160408-PC-S	●	●	●		●	●	●	●																																0,8	2,4
160412-PC-S	●	●	●		●	●	●	●																																1,2	2,2
160404-PC-M	●				●			●																								9,52	3,81	4,76	16,60	0,4	2,8				
160408-PC-M	●				●			●																																0,8	2,4
160412-PC-M	●				●			●																																1,2	2,2
160404-PC-M/4	●																																							0,4	4,4
160408-PC-M/4	●																																							0,8	4,2
160412-PC-M/4	●																																							1,2	4,0



# TURNING | ISO

TECHNOLOGY

TURNING

## VNGA

Standard tipped corners  
Sandwich tipped corners



MW




4 SC

insert size	uncoated				coated																dimensions																									
	PBC-10		PBC-15		PBC-25				PBC-40				PBC-10S				PBC-15S				PBC-25S				PBC-40S				d	d <sub>1</sub>	s	l	r	l <sub>1</sub>												
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D							E	F	G	H	A	B	C	D	E	F	G	H
160404-MW	●	●	●	●	●	●	●	●																																	9,52	3,81	4,76	16,50	0,4	5,0
160408-MW	●	●	●	●	●	●	●	●																																					0,8	4,4
160412-MW	●				●			●																																					1,2	3,9
160404-4SC									●		●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●					0,4	2,8	
160408-4SC									●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●					0,8	2,2		

GROOVING

## WBGW

Fullface




VM

insert size	uncoated				coated																dimensions																									
	PBC-10		PBC-15		PBC-25				PBC-40				PBC-10S				PBC-15S				PBC-25S				PBC-40S				d	d <sub>1</sub>	s	l	r	l <sub>1</sub>												
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D							E	F	G	H								
020102L-VM	●	●	●		●	●	●	●																																	3,97	2,30	1,58		0,2	4,8
020401L-VM	●	●	●		●	●	●	●																																					0,4	4,8

BORING

## WCGW

Fullface



VM

insert size	uncoated				coated																dimensions																									
	PBC-10		PBC-15		PBC-25				PBC-40				PBC-10S				PBC-15S				PBC-25S				PBC-40S				d	d <sub>1</sub>	s	l	r	l <sub>1</sub>												
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D							E	F	G	H								
020102-VM	●	●	●		●	●	●	●																																	3,97	2,30	1,58		0,2	2,7
020104-VM	●	●	●		●	●	●	●																																					0,4	2,7

MILLING




# TURNING ISO




## WNGA


Solid tipped corners



PC-S



PC-M




PC-M/4


insert size	uncoated				coated																dimensions									
	SBC1		SBC10		SBC25		SBC40		SBC-25C								SBC-40C													
	H	A	G	A	F	A	G	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>	
080404-PC-S	●	●	●	●	●	●	●																	12,70	5,13	4,76	8,50	0,4	2,8	
080408-PC-S	●	●	●	●	●	●	●																0,8					2,6		
080412-PC-S	●	●	●	●	●	●	●																1,2					2,4		
080404-PC-M	●		●		●		●																0,4					2,8		
080408-PC-M	●		●		●		●																0,8					2,6		
080412-PC-M	●		●		●		●																1,2					2,4		
080404-PC-M/4	●																						0,4					4,5		
080408-PC-M/4	●																						0,8					4,2		
080412-PC-M/4	●																						1,2					4,0		

## WNGA


Standard tipped corners  
Sandwich tipped corners



EW



MW



6 SC


insert size	uncoated				coated																dimensions																													
	PBC-10		PBC-15		PBC-25		PBC-40		PBC-10S				PBC-15S				PBC-25S				PBC-40S																													
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>				
080404-EW	●	●	●	●	●	●	●	●																																					12,70	5,13	4,76	8,50	0,4	3,1
080408-EW	●	●	●	●	●	●	●	●																													0,8	2,8												
080412-EW	●	●	●	●	●	●	●	●																													1,2	2,5												
080404-MW	●	●	●	●	●	●	●	●																													0,4	5,3												
080408-MW	●	●	●	●	●	●	●	●																													0,8	5,0												
080412-MW	●	●	●	●	●	●	●	●																													1,2	4,7												
080404-6SC					●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●									0,4	2,8												
080408-6SC					●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●									0,8	2,5												
080412-6SC					●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●									1,2	2,2												
080404W-6SC					●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●									0,4	2,8												
080408W-6SC					●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●									0,8	2,5												



# GROOVING | FormCut

## ■ BSAFR/L

Toolholder, external radial grooving




right hand shown

**Note:** For right-hand toolholders use right-hand inserts, for left-hand toolholders use left-hand inserts only.

designation		dimensions					
right-hand	left-hand	$h_1$	$h_2$	$b$	$f$	$L_1$	$L_2$
BSAFR 1616 - 12	BSAFL 1616 - 12	16	16	16	20	106	31
BSAFR 2020 - 12	BSAFL 2020 - 12	20	20	20	24	131	31
BSAFR 2525 - 12	BSAFL 2525 - 12	25	25	25	30	156	31
BSAFR 3225 - 12	BSAFL 3225 - 12	32	32	25	30	176	31


## ■ BSIFR/L

Toolholder, internal radial grooving



right hand shown

**Note:** For right-hand toolholders use left-hand inserts, for left-hand toolholders use right-hand inserts only.



designation		dimensions							
right-hand	left-hand	$h_1$	$h_2$	$b$	$f$	$L_1$	$L_2$	$D_{min.}$	
BSIFR 1616 - 12	BSIFL 1616 - 12	16	16	16	28	100	18	50	
BSIFR 2020 - 12	BSIFL 2020 - 12	20	20	20	32	125	18	72	
BSIFR 2525 - 12	BSIFL 2525 - 12	25	25	25	37	150	18	110	
BSIFR 3225 - 12	BSIFL 3225 - 12	32	32	25	37	170	18	110	

## ■ Spare parts


CLA 3103	SCR 1303	KEY 2104	VAR 5101

# GROOVING FormCut



## BFSN

External grooving




right hand shown

insert size	uncoated				coated																dimensions															
	PBC-10		PBC-15		PBC-10S				PBC-15S				PBC-25S				PBC-40S																			
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	W	T	r	r
BFSN-2,5-R/L	●				●																												2,5	4	0,2	
BFSN-3,0-R/L	●				●																												3,0	6	0,2	
BFSN-3,5-R/L	●				●																												3,5	6	0,2	
BFSN-4,0-R/L	●				●																												4,0	6	0,2	0,40
BFSN-4,5-R/L	●				●																												4,5	6	0,2	
BFSN-5,0-R/L	●				●																												5,0	6	0,2	0,40

## BFSV

External grooving and turning




right hand shown

insert size	uncoated				coated																dimensions															
	PBC-10		PBC-15		PBC-10S				PBC-15S				PBC-25S				PBC-40S																			
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	W	T	r	r
BFSV-3,0-R/L	●				●																												2,5	4	0,2	
BFSV-3,5-R/L	●				●																												3,0	6	0,2	
BFSV-4,0-R/L	●				●																												3,5	6	0,2	
BFSV-4,5-R/L	●				●																												4,0	6	0,2	
BFSV-5,0-R/L	●				●																												4,5	6	0,2	

## BFIN

Internal grooving



right hand shown

insert size	uncoated				coated																dimensions															
	PBC-10		PBC-15		PBC-10S				PBC-15S				PBC-25S				PBC-40S																			
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	W	T	r	r
BFIN-2,5-R/L					●	●																											2,5	3	0,2	
BFIN-3,0-R/L	●				●	●																											3,0	6	0,2	
BFIN-3,5-R/L	●				●	●																											3,5	6	0,2	
BFIN-4,0-R/L					●	●																											4,0	6	0,2	0,4
BFIN-4,5-R/L					●	●																											4,5	6	0,2	



# GROOVING | FormCut

TECHNOLOGY

TURNING


GROOVING

BORING

MILLING

## BFIV


Internal grooving and turning



insert size	uncoated				coated																dimensions																			
	PBC-10	PBC-15	PBC-25	PBC-40	PBC-10S				PBC-15S				PBC-25S				PBC-40S																							
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	W	T	r	r				
BFIV-3,0-R/L					●	●																															3,0	6	0,2	0,4
BFIV-3,5-R/L	●				●	●																															3,5	6	0,2	0,4
BFIV-4,0-R/L	●				●	●																															4,0	6	0,2	0,5
BFIV-4,5-R/L					●	●																															4,5	6	0,2	0,5
BFIV-5,0-R/L					●	●																															5,0	6	0,2	0,6

## BFRV



External copying



insert size	uncoated				coated																dimensions																			
	PBC-10	PBC-15	PBC-25	PBC-40	PBC-10S				PBC-15S				PBC-25S				PBC-40S																							
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	W	T	r	r				
BFRV-3,0-R/L	●				●	●																															3,0	6	1,50	
BFRV-3,5-R/L	●				●	●																															3,5	6	1,75	
BFRV-4,0-R/L	●				●	●																															4,0	6	2,00	
BFRV-4,5-R/L	●				●	●																															4,5	6	2,25	
BFRV-5,0-R/L	●				●	●																															5,0	6	2,50	

## BFDV


External profiling



insert size	uncoated				coated																dimensions																			
	PBC-10	PBC-15	PBC-25	PBC-40	PBC-10S				PBC-15S				PBC-25S				PBC-40S																							
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	W	T	r	r				
BFDV-0,2-R/L	●				●																																5	5	0,2	
BFDV-0,4-R/L	●				●																																5	5	0,4	
BFDV-0,8-R/L	●				●																																5	5	0,8	
BFDV-1,2-R/L	●				●																																5	5	1,2	

## BFTV

External threading  
(partial profile)





insert size	uncoated				coated																dimensions															
	PBC-10		PBC-15		PBC-10S				PBC-15S				PBC-25S				PBC-40S																			
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	W	T	r	r
BFTV-0,10-R/L	●				●	●																											5	5	0,10	
BFTV-0,14-R/L	●				●	●																											5	5	0,14	
BFTV-0,18-R/L	●				●	●																											5	5	0,18	
BFTV-0,21-R/L	●				●	●																											5	5	0,21	
BFTV-0,25-R/L	●				●	●																											5	5	0,25	
BFTV-0,28-R/L	●				●	●																											5	5	0,28	
BFTV-0,36-R/L					●	●																											5	5	0,36	
BFTV-0,43-R/L					●	●																											5	5	0,43	

Size of radius	Pitch P (max.)	Pitch P (min.)	Pitch P (average)
r = 0,10	P = 0,80	P = 0,69	P = 0,75
r = 0,14	P = 1,12	P = 0,97	P = 1,00
r = 0,18	P = 1,44	P = 1,25	P = 1,35
r = 0,21	P = 1,68	P = 1,46	P = 1,55
r = 0,25	P = 2,00	P = 1,74	P = 1,87
r = 0,28	P = 2,24	P = 1,95	P = 2,10
r = 0,36	P = 2,99	P = 2,50	P = 2,70
r = 0,43	P = 3,44	P = 2,99	P = 3,20

## Boring bars solid carbide



Design E...SEUP L/R



right hand shown

Right-hand boring bar with cylindrical solid carbide shank and internal coolant feed.

order number	insert	dimensions				
		$d_{min}$	$d^{97}$	f	$L_1$	g
E 06 F - SEUP L/R 04	EPH.. 0401..	6,8	6	3,4	80	9°
E 07 H - SEUP L/R 04	EPH.. 0401..	8,4	7	4,4	100	5°
E 08 H - SEUP L/R 04	EPH.. 0401..	9,5	8	4,9	100	5°
E 10 K - SEUP L/R 06	EPH.. 06T1..	11,5	10	5,8	125	5°
E 12 M - SEUP L/R 06	EPH.. 06T1..	13,5	12	6,9	150	3°
E 16 R - SEUP L/R 06	EPH.. 06T1..	18,5	16	9,8	200	0°



right hand shown

Right-hand boring bar with cylindrical solid carbide shank, two clamping surfaces and internal coolant feed.

order number	insert	dimensions							
		$d_{min}$	d	f	$L_1$	$L_2$	$d^{97}$	h	g
E 06 10 H - SEUP L/R 04	EPH.. 0401..	6,8	6	3,4	100	36	10	8	9°
E 07 10 K - SEUP L/R 04	EPH.. 0401..	8,4	7	4,4	125	42	10	8	5°
E 08 10 K - SEUP L/R 04	EPH.. 0401..	9,5	8	4,9	125	48	10	8	5°


## Spare parts

screws and keys					
order number	SCR 1101	SCR 1102	KEY 2101	KEY 2102	VAR 5101
suitable for	EPH 0401..	EPH 06T1..	SCR 1101	SCR 1102	







**EPHT**  
**EPHW**  
Fullface




positive-VM



Wiper-VM




VM




Wiper-VM

insert size	uncoated				coated																																dimensions										
	PBC-10		PBC-15		PBC-25		PBC-40		PBC-10S								PBC-15S								PBC-25S								PBC-40S								d		d <sub>1</sub>	s	l	r	l <sub>1</sub>
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>	
EPHT040102-VM			●		●																																				0,2						
EPHT040103-VM			●		●																																			0,3							
EPHT040104-VM			●		●																																			0,4							
EPHT040102R/L-W-VM					●																																		0,2								
EPHW040102-VM	●	●			●																																		0,2								
EPHW040103-VM	●	●			●																																		0,3								
EPHW040104-VM	●	●			●																																		0,4								
EPHW040102R/L-W-VM					●																																		0,2								
EPHW040103R/L-W-VM					●																																		0,3								
EPHW040104R/L-W-VM					●																																		0,4								


**EPHT**  
**EPHW**  
Standard tipped corners



positive-EW



Wiper-EW



EW




Wiper-EW

insert size	uncoated				coated																																dimensions										
	PBC-10		PBC-15		PBC-25		PBC-40		PBC-10S								PBC-15S								PBC-25S								PBC-40S								d		d <sub>1</sub>	s	l	r	l <sub>1</sub>
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r	l <sub>1</sub>	
EPHT06T102-EW	●				●																																			0,2	3,0						
EPHT06T104-EW	●				●																																			0,4	2,8						
EPHT06T102R/L-W-EW					●																																			0,2	3,0						
EPHW06T101-EW	●	●			●																																			0,1	3,1						
EPHW06T102-EW	●	●			●																																			0,2	3,0						
EPHW06T104-EW	●	●			●																																			0,4	2,8						
EPHW06T108-EW	●	●			●																																			0,8	2,4						
EPHW06T102R/L-W-EW					●																																		0,2	3,0							

## ■ Adapter sleeve

Boring bars design X...GEUP



Adapter sleeves enable versatile use of the boring bars in all areas.  
Coolant feed is provided through the adapter.

order number	for boring bars	dimensions				
		D	d	d <sup>H7</sup>	H	L
Adap - 1635	X 3,5 F-GEUP L/R	16	4	3,5	14	100
Adap - 1640	X 04 F-GEUP L/R	16	5	4,0	14	100
Adap - 1650	X 06 H-GEUP L/R	16	6	5,0	14	100
Adap - 1660	X 05 H-GEUP L/R	16	8	6,0	14	100



## X-GE R/L

Solide carbide boring bars with one clamping surface, brazed cutting edges and internal coolant feed. Adapter sleeve look left.



right hand shown

order number	uncoated				coated																dimensions								
	SBC1		SBC10		SBC25		SBC40		SBC-25C								SBC-40C												
	H	A	G	A	F	A	G	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	dg <sup>7</sup>	d <sub>min</sub>	f	l <sub>1</sub>	l <sub>2</sub>	r
X3,5F-GEUP-R/L		●	●	●	●																		3,5	4,0	2,0	80	12	0,1	
X3,5F-GEUP-R/L		●	●	●	●																							0,2	
X04F-GEUP-R/L		●	●	●	●																			4,0	5,0	2,5	80	14	0,1
X04F-GEUP-R/L		●	●	●	●																							0,2	
X04F-GEUP-R/L		●	●	●	●																							0,4	
X05H-GEUP-R/L		●	●	●	●																							0,1	
X05H-GEUP-R/L		●	●	●	●																			5,0	6,0	3,0	100	18	0,2
X05H-GEUP-R/L		●	●	●	●																							0,4	
X06H-GEUP-R/L		●	●	●	●																							0,1	
X06H-GEUP-R/L		●	●	●	●																			6,0	7,0	3,5	100	20	0,2
X06H-GEUP-R/L		●	●	●	●																							0,4	



# MILLING | ISO


## RDHX Fullface



VM

insert size	uncoated				coated																												dimensions												
	PBC-10		PBC-15		PBC-25		PBC-40		PBC-10S							PBC-15S							PBC-25S							PBC-40S															
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r
0702M0-VM	●		●		●		●																																	7,0	2,7	2,38			
1003M0-VM	●		●		●		●																																	10,0	3,8	3,18			
12T3M0-VM	●		●		●		●																																	12,0	3,8	3,97			

## SDHW-AEN Standard tipped corners



MW

insert size	uncoated				coated																												dimensions												
	PBC-10		PBC-15		PBC-25		PBC-40		PBC-10S							PBC-15S							PBC-25S							PBC-40S															
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r
1204AEN-MW	●						●																																	12,7	5,5	4,76	12,70		4,0



MW

## SPKN-EDR

Standard tipped corners

insert size	uncoated				coated																												dimensions												
	PBC-10		PBC-15		PBC-25		PBC-40		PBC-10S							PBC-15S							PBC-25S							PBC-40S															
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r
1203EDR-MW	●				●																																			12,7		3,18	12,7		4,0



MW

## TPKN-PDR

Standard tipped corners

insert size	uncoated				coated																												dimensions												
	PBC-10		PBC-15		PBC-25		PBC-40		PBC-10S							PBC-15S							PBC-25S							PBC-40S															
	A	F	A	C	A	D	A	E	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	A	B	C	D	E	F	G	H	d	d <sub>1</sub>	s	l	r
1603PDR-MW	●				●																																			9,52		3,18	16,50		4,0



cutting materials

ultrahard

## ■ Important Information

### Change of item description

Below we have listed the precise allocation of the old item description "F" and "T" to the new item description. Please bear in mind that the items have solely been renamed. Geometries have not been changed. You may still use the old item description in your orders. As of January 1, 2012 the inserts in question will bear the new item description when delivered.

Change of item description for the chamfer geometry of all uncoated PcBN-grades		
PcBN-grade	Geometry "OLD"	Geometry "NEW"
SBC - 1	T	H
	F	A
SBC - 10	T	G
	F	A
SBC - 25	T	F
	F	A
SBC - 40	T	G
	F	A
PBC - 10	T	F
	F	A
PBC - 15	T	C
	F	A
PBC - 25	T	D
	F	A
PBC - 40	T	E
	F	A

### Cutting length and cutting time

In order to fully exploit the performance of our PcBN cutting materials, measured by the number of parts produced, the following factors are crucial.

The total cutting length of a workpiece has to be calculated and observed. This varies enormously depending on the feed rate. Therefore the required surface finish has to be observed precisely (see pages 12 and 19). The real cutting length that can be achieved during hardturning is between 3,000 and 12,000 meters per cutting edge. The real cutting time per item determines the number of parts produced, and is controlled by the cutting speed and the feed rate. Thus the ideal aim for each workpiece to strive for is the lowest possible cutting length, the shortest cutting time at the highest possible cutting speed. Please refer to our diagrams on pages 14 to 17.

#### Cutting length in meters

$$SCL = \frac{Dm \times 3,14 \times lm}{1000 \times fn}$$

#### Operating duration in minutes

$$Tc = \frac{lm}{fn \times n}$$

**SCL** = Cutting length in meters  
(spiral cutting length)

**Dm** = Diameter in mm

**lm** = Turning length

**fn** = Feed rate per revolution in mm

**Vc** = Cutting speed in m/min

**n** = Spindle RPM

**Tc** = Operating duration in minutes



**Please observe our full range  
of tools with ultrahard cutting materials**



## ■ Imprint

© Becker Diamantwerkzeuge GmbH  
Benzstraße 13  
82178 Puchheim/München, Germany  
all rights reserved

Tel. +49 (0) 89 02 28-0  
Fax +49 (0) 89 02 28-30  
sales@beckerdiamant.de  
www.beckerdiamant.de

Conception and Design:  
Elke Peter Marketing + Werbung, Olching  
hr-design Rainer Herrmann, München

# PcBN

## Cutting Tools



ÁLAVA: Parque Empresarial Inbisa, Av. de los Olmos, Mod C, Pab 8	Tel.: 945 274 644	Fax: 945 274 766	01013 VITORIA
ASTURIAS: Pol. Ind. Bankuni6n, 2 La Siderurgia s/n.	Tel.: 985 322 010	Fax: 985 313 516	33211 GIJON - TREMAÑES
BARCELONA: Pol. Ind La Llagosta, Gaudí 42-48, Apartado 63	Tel.: 935 742 418	Fax: 935 601 707	08120 LA LLAGOSTA
GUIPÚZCOA: Bº Sta. Lucía s/n	Tel.: 943 729 070	Fax: 943 729 206	20709 EZKIO-ITSASO
MADRID: Camino de Hormigueras, 149	Tel.: 913 038 743	Fax: 917 788 776	28031 VALLECAS (Pueblo)
SEVILLA: Pol. Ind. El Pibo, parcela 121, Nave 3	Tel.: 955 630 032	Fax: 955 630 948	41710 BOLLULLOS DE LA MITACI6N
VALENCIA: Calle Olta, 29	Tel.: 963 733 603	Fax: 963 338 455	46006 VALENCIA
VIZCAYA: Jos6 Mº Ugarteburu, 7 Begoña	Tel.: 944 460 850	Fax: 944 466 481	48007 BILBAO
ZARAGOZA: Pol. Ind Cogullada C/ Tom6s A. Edison, 13	Tel.: 976 470 177	Fax: 976 471 123	50014 ZARAGOZA

[ayma@ayma.es](mailto:ayma@ayma.es)

<http://www.ayma.es>



[www.beckerdiamant.de](http://www.beckerdiamant.de)